

AD-A158 042

HOT ELECTRON EMISSION IN SEMICONDUCTORS(U) INSTITUT
FUER EXPERIMENTALPHYSIK INNSBRUCK (AUSTRIA)
E GORNIK ET AL. 15 JAN 85 R/D-4410-EE01

1/1

UNCLASSIFIED

DAJA45-84-C-0052


F/G 20/12

NL

END

FILMED

etc.



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

R+D-4410-EE-01

①

"HOT ELECTRON EMISSION IN SEMICONDUCTORS"

Principal investigator and contractor:

Prof. Dr. E. G o r n i k
Institut für Experimentalphysik
Schöpfstraße 41
A-6020 Innsbruck

AD-A158 042

Contract number: DAJA 45-84-C-0052

1st Interim Report
15 November 1984 - 15 January 1985

DTIC
ELECTE
S JUL 29 1985 D
G

"The Research reported in this document has been made possible through the support and sponsorship of the U.S. Government through its European Research Office of the U.S. Army. This report is intended only for the internal management use of the Contractor and the U.S. Government".

DISTRIBUTION STATEMENT A
Approved for public release
Distribution Unlimited

DTIC FILE COPY

"HOT ELECTRON EMISSION IN SEMICONDUCTORS"

1st Interim Report

15 November 1984 - 15 January 1985

Summary of the Scientific work

The research work on "hot electron emission in semiconductors" was started with the following topics:

- a) Electron heating in GaAs/GaAlAs single heterostructures
- b) The emission due to the interaction of drifting carriers in GaAs/GaAlAs heterostructures with a periodic grating
- c) FIR emission due to streaming of hot carriers in crossed electric and magnetic fields in p-Ge

ad a) The topic of carrier heating in the lateral transport of two-dimensional (2D) systems along semiconductor interfaces and heterojunctions has attracted much interest in the last years, especially due to the applications of these systems for fast field effect transistors¹ and, recently, for hot carrier and real space transfer devices². There are several theoretical papers³ on the problem of carrier heating in GaAs/AlGaAs heterojunctions.

We have performed FIR emission experiments by passing a lateral current through the 2D electron system of GaAs/AlGaAs single heterojunctions. This heats up the carriers to a carrier temperature T . It has been shown in the experiments of Shah et al.⁴ and in femtosecond studies of the intraband relaxation by Erskine et al.⁵ that the carriers thermalize very fast to a thermal distribution characterized by the carrier temperature T , via carrier-carrier interaction within less than 100 fs⁵. Since this

is by orders of magnitudes less than the energy relaxation time (10^{-10} to 10^{-9} s) the carrier system itself represents a system in thermal equilibrium.

We have investigated GaAs/AlGaAs heterojunctions with ultrahigh as well as low electron mobility. A relative method of determining the carrier heating in the electric field is introduced, which allows the measurement of T over a wide range of carrier temperatures ($10 \text{ K} \leq T \leq 150 \text{ K}$). This method uses two narrowband FIR detectors at 35 cm^{-1} (GaAs) and at 100 cm^{-1} (Ge:Ga) for the analysis.

The electron heating is found to increase nearly linearly with the input power and reaches 100 K when the input power exceeds 10^7 eVs^{-1} per electron. The values of heating for the three different samples are surprisingly close together although the electron concentration varies by a factor of three and the mobility by a factor of 100. The slopes of the curves are similar which indicates a very general heating law as found in Si-MOSFETs⁶.

- ad b) Two-dimensional electron systems represent ideal systems for observing optical transitions due to periodically accelerated motion ("Smith-Purcell-effect"⁷): (1) The carriers are confined near the surface and can be brought close to a periodic gate potential; (2) the carrier system is extremely degenerate and high Fermi velocities are present at simultaneously high mobilities giving extremely long mean free paths up to more than $1 \mu\text{m}$ at the Fermi surface.

We have estimated the emission intensity of a GaAs/AlGaAs heterostructure due to the free-carrier radiation by the motion of the electrons with velocity v near the Fermi surface along a periodic potential with amplitude ΔU and period (a) in a semi-classical model using the dipole radiation theory and Fermi-statistics for the transition probability.

The spectral intensity per frequency interval is for a realistic periodic potential of $\Delta U = 1$ mV in the order of 10^{-10} W/cm²cm⁻¹ and should therefore be observable. The intensity is proportional to the square of the periodic potential, and thus may reach values of up to μ W/cm²cm⁻¹. The experimental realisation is done by evaporating a semitransparent (NiCr) gate electrode upon a sinusoidal photoresist structure and applying small voltages and a "compensation" voltage along the gate in order to avoid pinch-off effects during the electric field heating of the 2D system. Reproducible results on this new source have not been obtained yet.

ad c) The work on emission due to streaming of hot carriers in p-Ge has been started by the preparation and characterization of the required p-Ge samples. Material with a doping level of $\sim 1 \times 10^{14}$ is used. Samples with the geometry $6 \times 2 \times 1$ mm³ were polished and contacted on the large surfaces by evaporating In and subsequent annealing at 300°C. Ohmic contacts were achieved and first emission experiments performed. Emission due to the hot hole distribution and a weak cyclotron resonance signal, similar to the results of Komiyama⁸ were obtained.

R.A. Höpfel

M. Helm

E. Gornik

Dr. R.A. Höpfel has taken a one year leave of absence to work with AT&T Bell Laboratories, Holmdel, N.J. He will be replaced as associate investigator by Mag. M. Helm. As additional research assistants G. Strasser and J. Smoliner will participate in the project.

References

- /1/ For a review see: T.P. Pearsall, Surf. Sci. 142, 524 (1984)
- /2/ S. Luryi, A. Kastalsky, A.C. Gossard, R. Hendel, Appl. Phys. Lett. (scheduled for Dec. 15, 1984) and references therein.
- /3/ e.g.: P.J. Price, Proc. 17th Int. Conf. on "The Physics of Semiconductors", San Francisco 1984 and references therein.
- /4/ J. Shah, A. Pinczuk, H.L. Störmer, A.C. Gossard, W. Wiegmann, Appl. Phys. Lett. 44, 322 (1984)
- /5/ H. Sakaki, K. Hirakawa, J. Yoshino, S.P. Svensson, Y. Sekiguchi, T. Hotta, S. Nishii, Surf. Sci. 142, 306 (1984)
- /6/ R.A. Höpfel, E. Vass, E. Gornik, Solid State Commun. 49, 501 (1984)
- /7/ S.J. Smith, E.M. Purcell, Phys. Rev. 92, 1069 (1953)
- /8/ S. Komiyama, Advances in Physics 31, 255 (1982)

Accession For	
NTIS	<input checked="" type="checkbox"/>
GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By <i>Per Form 50</i>	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
<i>A/1</i>	<i>44</i>



unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER	
	AD A158 042		
4. TITLE (and Subtitle)		5. TYPE OF REPORT & PERIOD COVERED	
Hot Electron Emission in Semiconductors		First Interim Report Nov. 84 - Jan. 85	
		6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s)		8. CONTRACT OR GRANT NUMBER(s)	
Prof. Dr. Erich Gornik Dr. Ralph Höpfel Mag. Manfred Helm		DAJA 45-84-C-0052	
9. PERFORMING ORGANIZATION NAME AND ADDRESS		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS	
Institut für Experimentalphysik Innsbruck, Austria			
11. CONTROLLING OFFICE NAME AND ADDRESS		12. REPORT DATE	
USARDSG-UK Box 65, FPO NY 09510		Jan. 15, 1985	
		13. NUMBER OF PAGES	
		4	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report)	
		unclassified	
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report)			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)			
18. SUPPLEMENTARY NOTES			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)			
<p>novel tunable FIR sources; hot electron emission in GaAs/GaAlAs heterostructures; and streaming of hot carriers in crossed electric and magnetic fields.</p>			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)			
<p>The hot electron emission from low and high mobility GaAs/GaAlAs hetero- structures was investigated in the FIR range at two frequencies. From the analysis a linear dependence of the electron temperature on input power per electron is found, nearly independent of the sample properties.</p> <p>The interaction of drifting carriers with periodic gratings in high mobility GaAs/GaAlAs systems is a promising scheme to obtain <u>DW</u> tunable FIR radiation.</p>			

DD FORM 1473 JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE

microwatt

unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

keywords include

20. No conclusive results have been obtained yet. The realization of streaming motion of hot carriers in p-Ge under crossed electric and magnetic fields is pursued at present.

• unclassified

END

FILMED

9-85

DTIC